




**BUREAU  
VERITAS**

# TEST REPORT

Technical Report: (7521)230-0102

Page 1 of 4  
August 26, 2021



Report Number  
(7521)230-0102

Zhejiang Bureau Veritas  
Consumer Products' Service  
Shenyue (Shaoxing) Co., Ltd  
1st-3rd Floor, No.4 Building,  
Kenan Commercial Building,  
Keyan Road, Keqiao, Shaoxing,  
Zhejiang. Post Code: 312000  
Tel: 86-0575-85677315.  
Fax: 86-0575-88620525  
website: cps.bureauveritas.com

This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.





**BUREAU  
VERITAS**

# TEST REPORT

LAB NO.: (7521)230-0102  
FORM NO.: /  
DATE IN: Aug 18, 2021  
MOD. DATE : Aug 23, 2021  
DATE OUT: Aug 26, 2021  
NO. OF WORKING DAYS: 4  
PAGE 2 OF 4

## OVERALL RATING

PASS

FAIL

DATA

X

Vendor:		Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	46607	Style No.:	/
Sample Description:	ONE PC OF WOVEN FABRIC	Style Description:	/
Color:	WHITE 00	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
SKU:	/		

Product Category	FABRIC
Test Requested	SELECT TEST
Previous Report No.	/

Submitted Fiber Content	91% RECYCLED POLYESTER 9% SPANDEX
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

C/N  
Zhejiang Bureau Veritas  
Consumer Products' Service  
Shenyue (Shaoxing) Co., Ltd  
1st-3rd Floor, No.4 Building,  
Kenan Commercial Building,  
Keyan Road, Keqiao, Shaoxing,  
Zhejiang Post Code: 312000  
Tel: 86-0575-85677315,  
Fax: 86-0575-88620525  
website: cps.bureauveritas.com

This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
UV PROTECTIVE PROPERTIES IN TEXTILE FABRICS			X	
LIQUID MOISTURE MANAGEMENT PROPERTIES OF FABRICS			X	

**Remark:** BVCPS (Shaoxing) contact information for this report

**General Information:**

Julie Yu (86)0575-85677409, Email: [Julie-b.yu@bureauveritas.com](mailto:Julie-b.yu@bureauveritas.com)  
Rebecca Ren (86)0575-85677410, Email: [rebecca.ren@bureauveritas.com](mailto:rebecca.ren@bureauveritas.com)

**Technical Questions:**

Terrance Chen (86)0575-85677315, Email: [terrance.chen@bureauveritas.com](mailto:terrance.chen@bureauveritas.com)  
Chasel Chen (86)0575-85677317, email: [chasel.chen@bureauveritas.com](mailto:chasel.chen@bureauveritas.com)

**BUREAU VERITAS**  
**CONSUMER PRODUCTS SERVICES ( SHAOXING )**

*Chasel Chen*

Chasel Chen  
**Operation Assistant Manager**



<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
<u>LIQUID MOISTURE MANAGEMENT PROPERTIES OF FABRICS</u> (AATCC 195-17e3)		
WETTING TIME - TOP - GRADE	5	/
WETTING TIME - BOTTOM - GRADE	5	/
ABSORPTION RATE - TOP - GRADE	3	/
ABSORPTION RATE - BOTTOM - GRADE	4	/
MAX WETTED RADIUS - TOP - GRADE	4	/
MAX WETTED RADIUS - BOTTOM - GRADE	5	/
SPREADING SPEED - TOP - GRADE	5	/
SPREADING SPEED - BOTTOM - GRADE	5	/
ACCUMULATIVE ONE-WAY TRANSPORT - GRADE	5	/
OVERALL MOISTURE MANAGEMENT CAPABILITY (OMMC) - GRADE	5	/

UV PROTECTIVE PROPERTIES IN TEXTILE FABRICS (AS/ NZS 4399)

PARAMETER:		
MEAN ULTRAVIOLET PROTECTION FACTOR (UPF)	79.9	/
UV - A TRANSMITTANCE (%) (MEAN)	0.352	/
UV - B TRANSMITTANCE (%) (MEAN)	0.970	/
RATED UPF	699	/
UPF RATINGS	50+	/
PROTECTION CATEGORY	EXCELLENT	/

\* REMARKS:

UPF RANGE	CLASSIFICATION	EFFECTIVE UVR PENETRATION, LESS THAN OR EQUAL TO (%)
15	MINIMUM	6.7
30	GOOD	3.3
50, 50+	EXCELLENT	2.0